



APPLICATION NOTE - SR009

Over Coating Silent Running

Silent Running may be over coated once it is dry and cured.

Most finish coatings can be applied over Silent Running, however, be sure to test a small area first to ensure there are no adverse reactions.

While Silent Running usually dries to the touch in approximately 1 hour, the cure time can take several days.

It is important to be sure to give ample time for Silent Running completely dry and cure prior to over coating. Any moisture trapped beneath a finish coat may cause the finish coat to lift or peel.

Minimum cure time is 4 days at 70° F and 50% RH.

If there are any question concerning the application of Silent Running, please contact us at the numbers below.

Current Inc.
30 Tyler Street
PO Box 120183
East Haven, CT 06512

Phone: 203-469-1337
Toll free: 877-436-6542
Fax: 203-467-8435